

# Technical Data Sheet



**Product name:** Centaur PP

Centaur PP is a lightweight and high-performance Polypropylene (PP) filament, which is engineered to have outstanding mechanical properties and a superb interlayer adhesion. Centaur PP combines a unique set of material properties into a 3D printer filament, which makes Centaur PP an extremely diverse and multi-functional material suitable for numerous applications ranging from 3D printing dishwasher proof and microwave safe household articles to functional engineering objects with great endurance properties.

Properties	Typical value	Test Method	Test condition
<b>Physical</b>			
Specific gravity	0.9 g/cc	ASTM D1505	-
Melt flow rate	8 g/10min	ISO 1133	260° C/5Kg
Water absorption	-	-	-
Moisture absorption	-	-	-
<b>Mechanical</b>			
Impact strength	-	-	-
Tensile strength	12Mpa	ASTM D638	@ Yield 2.0 in/min
Tensile modulus	-	-	-
Elongation at break	>600%	ASTM D638	@ Break 2.0 in/min
Flexural strength	-	-	-
Flexural modulus	402 Mpa	ASTM D790	1.27mm/min (0.05 inch/min)
Hardness	50D	ASTM D2240	Shore D Hardness
<b>Thermal</b>			
Print temperature	± 220 - 240° C	-	-
Melting temperature	± 205 ± 15° C	-	-
Viscat softening temp.	± 103° C	-	-
<b>Optical</b>			
Haze	-	-	-
Transmittance	-	-	-
Gloss	-	-	-

Product details, certifications and compliance	Diameter	Tolerance	Roundness	
HS Code	39169090	1.75mm	± 0.05mm	≥ 95%
REACH compliant	Yes	2.85mm	± 0.10mm	≥ 95%
RoHS certified	Yes			

All information supplied by or on behalf of Formfutura in relation to its products, whether in the nature of data, recommendations or otherwise, is supplied by request and in good faith, believed reliable, but Formfutura assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage or trade practice whatsoever in respect of application, processing or use made of the furnished information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties in any consequence from the use of all such information. Typical values are indicative only and are not to be considered as being binding specifications.